

**QUICK
ROOF**

COVER 'N COAT™

SELF-ADHESIVE REPAIR & REINFORCING FABRIC

***For Cracks,
Seams,
and Stress
Areas***



**Coat Immediately, No Waiting to Dry
For Roofing, Stucco, and EIFS
Construction**

One Step

**Easy To Use, Just Remove Release
Paper and Press In Place**



**COFAIR
PRODUCTS, INC.**

7301 N. St. Louis Avenue, Skokie, IL 60076 • 800-333-6700 • www.cofair.com



COVER 'N COAT™

SELF-ADHESIVE REPAIR & REINFORCING FABRIC

For Cracks, Seams and Stress Areas

COVER 'N COAT is a 35 mil membrane composed of a polyester fabric top surface and an aggressive rubberized asphalt adhesive layer.

INTENDED USE: Cover 'N Coat is an ideal repair and reinforcing material for cracks, seams, and stress areas in both metal and asphalt roofs. It can also be applied to joints in wood, gypsum board, metal, and polyethylene and styrene surfaces to form an air and moisture barrier in stucco and EIFS construction. Cover 'N Coat can also be used to seal around window and door openings. Its unique polyester surface is designed to adhere to roof coatings as well as the base coat in stucco/EIFS construction.

SURFACE PREPARATION: The surface must be clean, dry, and free from oil grease and debris. Dirty, rusty, or weathered surfaces

should be primed with a water, polymer, or solvent based primer prior to installation. Install when temperatures are 50°F or higher. If applying over caulking, make sure that the caulk is fully cured to prevent an adverse reaction with the asphalt adhesive.

INSTALLATION: Just remove release paper and press in place, making sure to center Cover 'N Coat over the area to be sealed. Roll to insure proper adhesion and to minimize any trapped air. When applying to concrete or masonry the surface must be primed before application of Cover 'N Coat. A construction grade spray adhesive can also be used to improve adhesion in less than ideal installation conditions. When overlapping from end to end, be sure to overlap a minimum of 4 inches. Do not leave the membrane exposed to direct sunlight for more than 30 days prior to coating.